

Products	Tg [oC]	Mw	Application
<b>MARCOATM CH460</b>	~70	14,000	MARCOATM CH460 is a high molecular weight solid polyester resin that provides excellent corrosion resistance for appliance primer in coil coating systems.
<b>MARCOATM CH462</b>	~60	15,000	MARCOATM CH462 is a high molecular weight solid polyester resin with high acid resistance and flexibility to formulate interior can coatings.
<b>MARCOATM CH470</b>	~70	17,000	MARCOATM CH470 is a high molecular weight solid polyester resin that provides both, hardness and flexibility for can coating systems.
<b>MARCOATM CH488</b>	~89	15,000	MARCOATM CH488 is a high molecular weight solid polyester resin with high reactivity and excellent acid resistance for interior can coating systems.
<b>MARCOATM CH489</b>	~89	15,000	MARCOATM CH489 is a high molecular weight solid polyester resin with high reactivity and excellent acid resistance for interior can coating systems.
<b>MARCOATM CH491</b>	~102	15,000	MARCOATM CH491 is a high molecular weight solid polyester resin with a high glass transition temperature and excellent acid resistance for interior can coating systems.
<b>MARCOATM CH492</b>	~104	15,000	MARCOATM CH492 is a high molecular weight solid polyester resin with a high glass transition temperature and excellent acid resistance for interior can coating systems.
<b>MARCOATM CH497</b>	~92	15,000	MARCOATM CH497 is a high molecular weight solid polyester resin with a high glass transition temperature and solubility in a broad range of organic solvents for interior can coating systems.
<b>MARCOATM CH541</b>	~47	16,000	MARCOATM CH541 is a high molecular weight solid polyester resin with excellent processibility and deep drawing for a broad range of coil and can coating systems.
<b>MARCOATM CH550</b>	~52	18,000	MARCOATM CH550 is a high molecular weight solid polyester resin with excellent processibility and deep drawing for a broad range of coil and can coating systems.
<b>MARCOATM CH554</b>	~52	15,000	MARCOATM CH554 is a high molecular weight solid polyester resin with good reactivity with phenolic resins to formulate interior can coatings.
<b>MARCOATM CH563</b>	~65	20,000	MARCOATM CH563 is a high molecular weight solid polyester resin with high reactivity for appliance primer in coil coatings and deep drawing can coatings.
<b>MARCOATM CL150</b>	~52	3,000	MARCOATM CL150 is a medium to low molecular weight solid polyester resin with excellent pigment dispersibility for appliance primer in coil coatings and can coatings.
<b>MARCOATM CL151</b>	~58	3,000	MARCOATM CL151 is a medium to low molecular weight solid polyester resin with high curing density for appliance primer in coil coatings and can coatings.

Products	Tg [oC]	Mw	Application
<b>MARCOATM CL250</b>	~58	5,000	MARCOATM CL250 is a medium to low molecular weight solid polyester resin with excellent hardness and stain resistance in a broad range of coil coatings applications, as well as, can coatings.
<b>MARCOATM CL270</b>	~78	6,000	MARCOATM CL270 is a medium to low molecular weight solid polyester resin to improve flexibility and hardness for solvent-borne can and coil coatings.
<b>MARCOATM CL271</b>	~71	4,500	MARCOATM CL271 is a medium to low molecular weight solid polyester resin with high curing density and excellent adhesion to aluminum for can coatings applications.
<b>MARCOATM CL331</b>	~38	9,000	MARCOATM CL331 is a medium to low molecular weight solid polyester resin with outstanding corrosion resistance for solvent-borne coil coating systems.

<sup>1</sup> Typical values, not for specification purposes