

Product	Effective Density [g/cm <sup>3</sup> ]	Average Particle size [μm]	Particle Size [μm] (Malvern)	Pressure Resistance Isostatic [Psi]	Pressure Resistance Isostatic [Mpa]
<b>Q-CEL® 300</b>	0.21	90	5 - 200	500	3.4
<b>Q-CEL® 6014</b>	0.14	85	5 - 200	250	1.7
<b>Q-CEL® 6019</b>	0.19	75	5 - 175	500	3.4
<b>Q-CEL® 6019S</b>	0.19	70	5 - 150	500	3.4
<b>Q-CEL® 6020FPS</b>	0.2	45	5 - 90	500	-
<b>Q-CEL® 6717</b>	0.19	52	5 - 105	500	3.4
<b>Q-CEL® 5028</b>	0.25	75	5 - 120	750	5.2
<b>Q-CEL® 6028</b>	0.28	70	5 - 150	750	-
<b>Q-CEL® 6036</b>	0.36	60	5 - 125	1,000	6.8
<b>Q-CEL® 6042S</b>	0.42	50	5 - 90	2,000	13.8
<b>Q-CEL® 6048</b>	0.48	50	5 - 100	3,000	20.7
<b>Q-CEL® 5070S</b>	0.7	35	10 - 100	3,500	24.2
<b>Q-CEL® 5019</b>	0.19	72	5 - 150	500	-
<b>Q-CEL® 5032S</b>	0.32	63	5 - 150	1,000	-
<b>Q-CEL® 7019</b>	0.19	80	5 - 150	500	3.4
<b>Q-CEL® 7023S</b>	0.23	85	5 - 120	750	5.2
<b>Q-CEL® 7028</b>	0.27	75	5 - 120	1,000	-
<b>Q-CEL® 7036</b>	0.36	63	5 - 125	1,000	-
<b>Q-CEL® 7040S</b>	0.4	54	5 - 100	2,000	13.8

The stated values correspond to typical values and hence do not represent a specification.