

Products	Average Particle Size [μm]	Polymer	Effective Density [g/cm^3]	Solids content [%]	Solvent resistance
F-30E	30 - 60	VC/AN-Copolymer	0.020 - 0.030	9 - 13	•
F-50E	40 - 60	Acrylnitril-Copolymer	0.020 - 0.040	11 - 16	••
F-65E	40 - 60	Acrylnitril-Copolymer	0.020 - 0.030	9 - 13	••

Solvent resistance: low: • medium: •• well suited: •••