

Grade LUVOMAG®	Origin		Purity [wt %]					Remarks
	Syn.	Nat.	Mg(OH) ₂	CaO	SiO ₂	Fe ₂ O ₃	Lol	
H 002	•		99.2			0.02		BET 10 m ² /g
H 015	•		99.0	0.45	0.12	0.04		BET 10 m ² /g
H 110	•		96.5	0.70	0.10	0.07	31.5	
H 257		•	95.3	2.1	3.7	0.50	31.0	Coated and var. milled grades available
Brucite		•	92.5	3.0	5.5	0.35	30.0	Various granular and milled grades available

Lol: loss on ignition.

Further grades and property details available upon request.