

<b>Product</b>	<b>Iodine Absorption Number [mg/g] acc. to ASTM D 1510</b>	<b>Oil Adsorption Number [ml/100g] acc. to ASTM D 2414</b>	<b>Tint strength acc. to ASTM D 3265</b>
<b>LUVOMAXX® M 450 *</b>	125 ± 8	111 ± 8	115 ± 8
<b>LUVOMAXX® M 451 *</b>	125 ± 8	92 ± 8	120 ± 8
<b>LUVOMAXX® M 360</b>	70 ± 8	123 ± 8	85 ± 8
<b>LUVOMAXX® M 361</b>	45 ± 8	117 ± 8	60 ± 8
<b>LUVOMAXX® M 3810</b>	51 ± 8	122 ± 8	55 ± 8
<b>LUVOMAXX® M 3710</b>	68 ± 8	126 ± 8	60 ± 8

\* grades with sieve residue (@325 mesh) of max. 10 ppm, all other grades show typical sieve residue of max 20 ppm