

Product	Appearance	Specific surface area BET [m ² /g]	Ash content [%]	Sieve residue > 45µm [%]	pH value
LUVOMAXX[®] Silica HM 1160	White powder	145 - 175	≤ 6	≤ 0.5	5 - 8
LUVOMAXX[®] Silica HM 2160	White granules	145 - 175	≤ 6	≤ 0.5	5 - 8
LUVOMAXX[®] Silica HM 1170	White powder	160 - 190	≤ 6	≤ 0.5	5 - 8
LUVOMAXX[®] Silica HM 2170	White granules	160 - 190	≤ 6	≤ 0.5	5 - 8
LUVOMAXX[®] Silica HM 1180	White powder	165 - 195	≤ 6	≤ 0.5	5 - 8
LUVOMAXX[®] Silica HM 2180	White granules	165 - 195	≤ 6	≤ 0.5	5 - 8