

<b>Product</b>	<b>Appearance</b>	<b>Active ingredient</b>	<b>Gas yield (ml/g)</b>	<b>Decomp. temperature (°C)</b>
<b>LUVOPOR® AT 6100</b>	Yellow powder	System, based on azodicarbonamide	280	150
<b>LUVOPOR® 9509</b>	Yellow powder	ZnO-activated azodicarbonamide	165	190