

Product (Elastomer grade)	Appearance	Chlorine content (%)	Mooney ML (1+4) @125°C
LUVOMAXX® CM 3055	white powder	29 - 31	50 - 60
LUVOMAXX® CM 3645	white powder	35 - 37	40 - 50
LUVOMAXX® CM 3650	white powder	35 - 37	45 - 55
LUVOMAXX® CM 3660	white powder	35 - 37	55 - 65
LUVOMAXX® CM 3665	white powder	35 - 37	60 - 70
LUVOMAXX® CM 3675	white powder	35 - 37	70 - 80
LUVOMAXX® CM 3680	white powder	35 - 37	75 - 85
LUVOMAXX® CM 3685	white powder	35 - 37	80 - 90
LUVOMAXX® CM 3690	white powder	35 - 37	85 - 95
LUVOMAXX® CPE 135A (Impact modifier)	white powder	35 - 37	< 60 (Hardness Shore A)
LUVOMAXX® CPE 135C (Impact modifier)	white powder	31 - 33	< 65 (Hardness Shore A)