

<b>Carboxylated Styrene Butadiene Latex</b>	<b>Styrene (%)</b>	<b>Brookfield Viscosity (20 rpm, 25°C, mPa.s)</b>
EUOPRENE® Latices 405	40	300
EUOPRENE® Latices 406	40	300
EUOPRENE® Latices 440	60	300
EUOPRENE® Latices 455	47	300
EUOPRENE® Latices 5583	40	300
EUOPRENE® Latices 5584	60	400
EUOPRENE® Latices 5585	47	300
EUOPRENE® Latices 5587	75	600
EUOPRENE® Latices 5588	50	350
EUOPRENE® Latices 8435	69	600
EUOPRENE® Latices 8487	67	500