

# LUVOCOM® 3F eco PET 50291 BK

Polyethylene terephthalate  
 unreinforced, based on 90% recycled PET, black

Physical properties		Test method	Specimen	Units	Typical value
Specific gravity		ISO 1183		g/cm <sup>3</sup>	1,36
Water absorption	23°C / 24h	ISO 62	ISO 3167 A	%	< 0,3

Mechanical properties at 23°C / 50% rh					
Tensile strength	dry, @50 mm/min	ISO 527	ISO 3167 A	MPa	55
Elongation @Fmax.	dry, @50 mm/min	ISO 527	ISO 3167 A	%	2,2
Tensile modulus	dry, @1 mm/min	ISO 527	ISO 3167 A	GPa	3
Flexural strength	dry, @10 mm/min	ISO 178	ISO 3167 A	MPa	75
Flexural elongation @Fmax.	dry, @10 mm/min	ISO 178	ISO 3167 A	%	2,4
Flexural modulus	dry, @2 mm/min	ISO 178	ISO 3167 A	GPa	3
Impact strength	dry	ISO 179 1eU	80x10x4mm	kJ/m <sup>2</sup>	28

Thermal properties					
Service temperature	during lifetime max. 200h		ISO 3167 A	°C	125

## Main features

Easy to print.

# LUVOCOM® 3F eco PET 50291 BK

Polyethylene terephthalate  
 unreinforced, based on 90% recycled PET, black

## Recommended processing parameters

### General

3D Printing parameters may vary from machine to machine. The following settings may be used as an indication: nozzle temperature: 245 - 270 °C / nozzle material: abrasion resistant / print bed temperature: > 50 °C / layer thickness: > 0,2mm / printing speed 40 - 60 mm/s.

The processing notes provided merely represent a recommendation for general use. Due to the large variety of machines, geometries and volumes of parts, etc., it may be necessary to employ different settings according to the specific application. Please contact us for further information.

### Delivery form & storage

Unless indicated otherwise, the material is delivered as 3mm long pellets in sealed bags on pallets. Preferably storage should be effected in dry and normally temperatured rooms.

### Predrying

It is advisable to predry the granules with a suitable dryer immediately before processing. The granule may absorb moisture from the environment.

Dryer type	Temperature °C	Drying time in h
Dehumidifying dryer	120	2 - 5
or	80	6 - 8

### Recommended processing parameters

In general LUVOCOM® 3F can be processed on conventional extrusion machines while observing the usual technical guidelines. Any added fibrous materials or fillers may have an abrasive effect. In this case the cylinder, screw and die should be protected against wear as is usual in the processing of reinforced thermoplastic materials. Lengthy dwell times for the melts in the cylinder should be avoided. Lower the temperatures during interruptions!

Melt temperature	Nozzle	Zone 3	Zone 2	Zone 1
280 °C	250 - 290 °C	260 - 300 °C	260 - 300 °C	260 - 300 °C

### Additional information

Filaments produced from this material may be wound into standard size spools.

50291 17 06 21

#### Europe and Head Office

Lehmann&Voss&Co. KG  
 Alsterufer 19  
 20354 Hamburg  
 Germany  
 Tel +49 40 44 197-0  
 Email: [luvocom@ehvoss.de](mailto:luvocom@ehvoss.de)

#### North America

LEHVOSS North America Inc.  
 185 South Broad Street  
 Pawcatuck, CT 06379  
 USA  
 Tel +1-855-681-3226  
 Email: [info@ehvoss.us](mailto:info@ehvoss.us)

#### Asia

LEHVOSS (Shanghai) Chemical Trading Co., Ltd.  
 Unit 4805, 8 Xingyi Road  
 Changning District, Shanghai 200336  
 China  
 Tel +86 21 62785181  
 Email: [info@ehvoss.cn](mailto:info@ehvoss.cn)

